

**ATTAR TEST REPORT NUMBER: 08/2689**

This document is issued in accordance with NATA's accreditation requirements. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards. Accredited for compliance with ISO/IEC 17025.

27 October 2008

Total Pages: 2**OIL-WET RAMP SLIP RESISTANCE**

Job No: M08/2689

Prepared for:	Ecoglo Ltd P.O. Box 8654 CHRISTCHURCH NEW ZEALAND	
Attention:	Mr. Mark Watson	
Test Site:	ATTAR, Unit 12, 134 Springvale Road, Springvale.	
Test Date:	23 October 2008	
Manufacturer:	Ecoglo Ltd	
Test Specimen, Size & Quantity Received:	Ecoglo N1070 slip resistant strip, 51x600 mm, 22 off supplied.	
Sampling & Direction of Testing:	Sampling conducted by client. Testing conducted as shown in Figure 1.	
Test Personnel:	Simon Langdon & Callum Oakey	
Preparation:	As received, fastened to 1200x600x12 mm particle board for testing.	
Joint Width:	N/A	
Air Temperature:	20°C	
Test Standard:	AS/NZS 4586 - 2004 Slip resistance classification of new pedestrian surface materials – Appendix D.	
Surface Structure :	Structured.	
Classification Criteria: (TABLE D3 in AS/NZS 4586- 2004)	Corrected Mean Overall Acceptance Angle	Slip Resistance Assessment Group
	6° to 10°	R9
	Over 10° to 19°	R10
	Over 19° to 27°	R11
	Over 27° to 35°	R12
	Over 35°	R13
Displacement Space:	Not Measured	
Displacement Space Assessment Group:	N/A	
Mean Overall Acceptance Angle:	33.6°	
Slip Resistance Assessment Group:	R12	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip-resistance be checked.

NOTE: Any specimens supplied will be disposed of in two (2) months time, unless otherwise instructed.

ATTAR

Simon Langdon
Engineering Technician
Approved Signatory

This report may not be reproduced except in its entirety.



Figure 1: General view of Ecoglo N1070 slip resistant strips fastened to particle board for testing. Arrow indicates direction of testing..